

Curtainboard™ 80

Physical Properties Data Sheet



PowerWool™ Curtainboard™ 80 is a higher-density semi-rigid mineral wool insulation board designed for demanding curtain wall systems, providing dependable fire protection, thermal performance, and long-term durability.



Approved for use in
Canada and the USA

CHARACTERISTIC	RESULT	TEST STANDARD																																																						
Compliance	Mineral Fiber Block and Board Thermal Insulation - Compliant Mineral Fiber Thermal Insulation for Buildings - Compliant	ASTM C612 CAN/ULC S702.1																																																						
Reaction to Fire	Flame spread index = 0; Smoke developed index = 0 Flame spread index = 0; Smoke developed index = 0 Determination of Non Combustibility of Building Materials - Non Combustible Behaviour of materials at 750°C - Non Combustible	ASTM E84 (UL 723) CAN/ULC S102 CAN/ULC S114 ASTM E136																																																						
Density	8 lbs/ft³ (128 kg/m³) - Nominal	ASTM C303																																																						
Dimensional Stability	Linear Shrinkage = Pass @1200°F (650°C)	ASTM C356																																																						
Corrosion Resistance	Corrosion of Steel - Passed	ASTM C665																																																						
Thermal Resistance	R-Value / inch @ 75°F RSI value / 25.4 mm @ 24°C	4.2 hr.ft².F/Btu 0.74 m²K/W ASTM C518																																																						
Reaction to Moisture	Moisture Sorption - Pass Water Vapor Transmission, Desiccant Method - 1670ng/Pa.s.m² (29 perm) Determination of Fungi Resistance - Passed	ASTM C1104 ASTM E96 ASTM C1338																																																						
Dimensions	1" (25.4 mm) to 8" (203.2 mm) in ½" increments 16" x 48" (406 mm x 1219 mm) 24" x 48" (610 mm x 1219 mm)																																																							
Acoustic Performance	<table><tr><th></th><th>125Hz</th><th>250Hz</th><th>500Hz</th><th>1000Hz</th><th>2000Hz</th><th>4000Hz</th><th>NRC</th><th>SAA</th></tr><tr><td>1.5"</td><td>0.09</td><td>0.47</td><td>0.97</td><td>1.04</td><td>0.99</td><td>0.98</td><td>0.85</td><td>0.88</td></tr><tr><td>2"</td><td>0.26</td><td>0.88</td><td>1.12</td><td>1.06</td><td>0.99</td><td>1.00</td><td>1.00</td><td>1.01</td></tr><tr><td>2.5"</td><td>0.39</td><td>1.06</td><td>1.15</td><td>1.06</td><td>1.02</td><td>1.07</td><td>1.05</td><td>1.06</td></tr><tr><td>3"</td><td>0.57</td><td>1.12</td><td>1.14</td><td>1.03</td><td>1.02</td><td>1.02</td><td>1.10</td><td>1.07</td></tr><tr><td>4"</td><td>0.76</td><td>1.13</td><td>1.09</td><td>1.03</td><td>1.01</td><td>1.04</td><td>1.05</td><td>1.06</td></tr></table>		125Hz	250Hz	500Hz	1000Hz	2000Hz	4000Hz	NRC	SAA	1.5"	0.09	0.47	0.97	1.04	0.99	0.98	0.85	0.88	2"	0.26	0.88	1.12	1.06	0.99	1.00	1.00	1.01	2.5"	0.39	1.06	1.15	1.06	1.02	1.07	1.05	1.06	3"	0.57	1.12	1.14	1.03	1.02	1.02	1.10	1.07	4"	0.76	1.13	1.09	1.03	1.01	1.04	1.05	1.06	ASTM C423-23 ASTM E795-23
	125Hz	250Hz	500Hz	1000Hz	2000Hz	4000Hz	NRC	SAA																																																
1.5"	0.09	0.47	0.97	1.04	0.99	0.98	0.85	0.88																																																
2"	0.26	0.88	1.12	1.06	0.99	1.00	1.00	1.01																																																
2.5"	0.39	1.06	1.15	1.06	1.02	1.07	1.05	1.06																																																
3"	0.57	1.12	1.14	1.03	1.02	1.02	1.10	1.07																																																
4"	0.76	1.13	1.09	1.03	1.01	1.04	1.05	1.06																																																

! For exterior use only. Not for interior walls.



Suitable for substitution in approved ASTM E119
1-hour and 2-hour fire-rated wall assemblies and
approved NFPA 285 exterior wall assemblies.*

*Per Priest & Associates Engineering Evaluation Letter EEL-11851 Rev. 2.

EVALUATED TO:	
CAN/ULC S702.1 Type 1 Compliant	ASTM C612 Type IVB Compliant
CAN/ULC S102 FSI: 0 SDI: 0	ASTM E84 (UL 723) FSI: 0 SDI: 0
CAN/ULC S114 Classified Non-Combustible	ASTM E136 Classified Non-Combustible
ASTM C1338 Does not support fungi growth.	


C FILE: B1124

PowerWool Insulation Inc. has no control over the workmanship, design of installation, accessories used with or conditions of application, and as such we do not warranty the performance or results of any installation containing PowerWool Insulation Inc.'s products.

All information on this technical data sheet is based on data considered to be accurate, tested in laboratories and is published for the user's investigation, consideration, and verification only. Nothing written herein represents a warranty or guarantee for which the manufacturer or distributor may be held responsible legally. No responsibility for assumptions or misrepresentation is assumed by the publisher.